







### Product properties

<b>Format</b>	2200* x 185 x 13 mm	
Top layer	ca. 3.6 mm	
<b>Packaging</b>	Pack	9 Elements / 3.663 m <sup>2</sup> / 29.304 kg
	Pallet	32 Packs / 117.216 m <sup>2</sup> / 937.728 kg
<b>Guarantee (according to Parador guarantee conditions)</b>		25 years (private use) 10 years (commercial use)
Notes	*1 joint length permitted per package - cleaning and maintenance see instructions - technical changes reserved	

### Product labelling






 EN 14342:2013		 CERTIFIED BY SCS Global Services	 www.blauer-engel.de/uz176	
 Quality Production Controlled Functionality www.tuv.com ID: 0600067515	 PEFC® PEFC/04-31-0507	 THIRD-PARTY VERIFIED ISO 14025 and EN 15064 Institut Bauen und Umwelt e.V.		

\*not valid for smoked products.




### Tolerances (EN 13489)

Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.2 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.2 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

### Classification general product features

	Test method	Rating
 Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
 Effect of a furniture leg	EN 424	No visible changes
 <b>Thermal resistance</b> Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	0.087 m <sup>2</sup> *K/W
 Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm
 Acoustical - Impact noise reduction	ISO 717-2	18 dB (with Akustik-Protect 100)
Disposal		EAK-Code-number 20 01 38

### Classification surface characteristics

	Test method	Rating	
		Lacquer	Natural oiled plus
 Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.49
	CEN/TS 15676	29 SRT (SRV wet)	99 (USRV)
51 SRT (SRV dry)			
 Reaction to fire, click-installation as a floating floor	EN 13501-1	D <sub>fl</sub> s1	
	EN 13501-1	D <sub>fl</sub> s1	
 Chemical resistance	EN 13442:2023 Annex B	Category 5	Category 5
Bond strength / Gross cut test	ISO 2409	0	n.n.
Slip resistance, inclined plane	EN 16165, Annex B	R 9	R 10

Changed:	QMB	File name:	PA TDS Parkett Classic-3060 EN 20231201
Date:	01.08.2013	Latest update at:	<a href="https://parador.de/en/pcms/downloads/downloadfile/file_id/211/">https://parador.de/en/pcms/downloads/downloadfile/file_id/211/</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023

Free sorting according to EN 13489							
Assortment:	Block						
Characteristics according to EN 1310:	Upper side of the lamella						
Type of wood:	European maple	Beech		Oak			
Botanical designation / Code (EN 13556):	Acer pseudoplatanus L. / ACPS	Fagus sylvatica L. / FASY		Quercus petraea Liebl., Quercus robur L. / QCXE			
Shortcut / sorting (internal):	ER-L-BAH	ER-L-BU		ER-L-EI			
	Version 3 2012	Version 7 2019		Version 13 2019			
Grade:	Natur	Natur	Living	Select	Natur	Living	Living knotty
Sound sapwood	-			not permitted		permitted up to 75% of the lamella / up to 50% per top layer also slightly discoloured	permitted (also slightly discoloured)
Knot (intergrown)	permitted: up to 10mm		permitted: up to 20 mm	not permitted			permitted: up to 30 mm
Falling out knot	not permitted					permitted: up to 20 mm	
Pinkknots	permitted			not permitted	permitted: up to 6 mm	permitted: up to 30 mm	permitted: clusters of knots
Filling	permitted			not permitted	permitted		
Slight cracks / hairline cracks	not permitted						
Sugar inclusions, mineral inclusions	permitted: colour inclusions up to 80 mm		permitted: colour inclusions	-			
Bark pocket	not permitted						
Lightning cracks	not permitted					permitted	
Slope of grain	no criterion						
Healthy heart	permitted		permitted: up to 100%	-			permitted
Medullary ray	not permitted						
Discoloration, colour variation	permitted: all colours, slight discoloration	permitted: all colours, light inlets	permitted: all colours, slight discoloration	permitted: slight colour variations	permitted: all colours, slight discoloration		
White streaks	-			not permitted	permitted		
Pilling sticks marking	not permitted						
Biodeterioration (EN 1311)	not permitted					permitted: wormholes	not permitted
Non-visible parts							
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.							
Comment							
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.							

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3060_Anhang_EN_20231201
Date:	01.05.2013	Latest update at:	<a href="https://parador.de/en/pcms/downloads/downloadfile/file_id/211/">https://parador.de/en/pcms/downloads/downloadfile/file_id/211/</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023
			Page 1 of 3

Free sorting according to EN 13489			
Assortment:	Block		
Characteristics according to EN 1310:	Upper side of the lamella		
Type of wood:	Ash	American walnut	
Botanical designation / Code (EN 13556):	Fraxinus excelsior L., Fraxinus angustifolia / FXEX	Juglans nigra L. / JGNG	
Shortcut / sorting / (internal):	ER-L-ES	ER-L-SWN	
	Version 11 2022	Version 5 2015	
Grade:	Living	Natur	Living
Sound sapwood	-	permitted	
Knot (intergrown)	permitted: up to 30 mm		
Falling out knot	not permitted		
Pinkknots	permitted: up to 5 mm		permitted: up to 10 mm
Filling	permitted		
Slight cracks / hairline cracks	not permitted		permitted
Sugar inclusions, mineral inclusions	permitted	-	permitted
Bark pocket	not permitted		
Lightning cracks	not permitted		permitted
Slope of grain	no criterion		
Healthy heart	permitted: black core up to 75% of a lamella / brown lamellas up to 70% per plank	-	
Medullary ray	permitted	-	
Discoloration, colour variation	permitted: all colours / discolorations	permitted: all colours	
White streaks	not permitted	-	
Pilling sticks marking	not permitted		
Biodeterioration (EN 1311)	not permitted		
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3060_Anhang_EN_20231201
Date:	01.05.2013	Latest update at:	<a href="https://parador.de/en/pcms/downloads/downloadfile/file_id/211/">https://parador.de/en/pcms/downloads/downloadfile/file_id/211/</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023
			Page 2 of 3

Free sorting according to EN 13489

Assortment:		Wide plank					
Characteristics according to EN 1310:		Upper side of the plank					
Type of wood:		Oak				Ash	Larch
Botanical designation / Code (EN 13556):		Quercus petraea Liebl., Quercus robur L. / QCXE				Fraxinus excelsior L., Fraxinus angustifolia / FXEX	Larix decidua Mill. / LADC
Shortcut / sorting (internal):		EI-GÜ-LHD Version 4 2022				ER-LH-ES Version 3 2021	ER-LH-LÄR Version 2 2017
Grade :	Select	Natur	Living	Living Plus	Rustikal	Living	Rustikal
Sound sapwood	not permitted		permitted	not permitted		-	permitted
Knot (intergrown)	permitted: up to 15 mm	permitted: up to 30 mm	permitted: up to 50 mm		permitted: up to 80 mm	permitted: up to 30 mm	permitted: up to 50 mm
Falling out knot	not permitted	permitted: up to 25 mm	permitted: up to 25 mm		permitted: up to 60 mm	permitted: up to 15 mm	permitted: up to 25 mm
Pinkknots	permitted	permitted	permitted: cluster of knots			permitted	
Filling	permitted						
Slight cracks / hairline cracks	not permitted	permitted				not permitted	permitted
Sugar inclusions, mineral inclusions	-				permitted	not permitted	permitted: resin galls
Bark pocket	not permitted				permitted	not permitted	permitted
Lightning cracks	permitted: in knots				permitted	permitted	permitted: in knots
Slope of grain	no criterion						
Healthy heart	not permitted				permitted	permitted: black core up to 70% of a plank / up to 30 % of planks	-
Medullary ray	permitted						
Discoloration, colour variation	permitted: slight colour variations				permitted: all colours		permitted: slight colour variations
White streaks	not permitted	permitted				-	
Pilling sticks marking	not permitted						
Biodeterioration (EN 1311)	not permitted						
<b>Non-visible parts</b>							
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.							
<b>Comment</b>							
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.							

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3060_Anhang_EN_20231201
Date:	01.05.2013	Latest update at:	<a href="https://parador.de/en/pcms/downloads/downloadfile/file_id/211/">https://parador.de/en/pcms/downloads/downloadfile/file_id/211/</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023
			Page 3 of 3